

BI-FUNCTIONAL DYES	Dyeing Shade		Light		Solubility	Washing		Perspiration				Chlorinate Water	Rubbing	
			AATCC	ISO		Effect	Stain	Acid		Alkali			Dry	Wet
	3%	6%						Effect	Stain	Effect	Stain			
ITOFIX YELLOW 4GL 150% (YELLOW 160)			5	5	150	4	4	4-5	4-5	4-5	4-5	4-5	5	3-4
ITOZOL YELLOW BF4R 150% (YELLOW 145)			5	5	180	4-5	4-5	4-5	4-5	4-5	4-5	4-5	5	4
ITOFIX YELLOW 3RS 150% (YELLOW 145)			5	5	150	4-5	4	4	4	4	4	4	5	4
ITOFIX G. YELLOW MERL 150% (YELLOW 145)			5	5	150	4-5	4	4	4	4	4	4	5	4
ITOFIX ORANGE 2RN 150% (ORANGE 122)			4	4	100	4	4	4	4	4	4	3-4	5	3
ITOFIX SCARLET 2GD 150%			4-5	4-5	100	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	3
ITOZOL RED BF2B 150% (RED 195)			4	4	180	4-5	4-5	4-5	4-5	4	4	4	4-5	4
ITOFIX RED 3BS 150% (RED 195)			4	4	150	4-5	4	4	4	4	4	4	4-5	4
ITOFIX RED ME4BL 150% (RED 195)			4	4	150	4-5	4	4	4	4	4	4	4	4
ITOFIX RED GD 150% (RED 223)			4	4	150	4-5	4-5	4/5	4-5	4	4	4-5	5	3-4
ITOFIX BLUE BRF 150% (BLUE 221)			5	5	150	5	4	4/5	4	4/5	4	3	5	3
ITOFIX NAVY BLUE BF (BLUE 222)			4-5	4-5	150	5	4	4/5	4	4	4	4	5	3-4
ITOFIX NAVY BLUE SFB (BLUE 222)			4-5	4-5	150	5	4-5	4/5	4/5	4/5	4-5	4	5	3-4

